



# CERTIFICATO DI COLLAUDO

## INSPECTION CERTIFICATE

SECTION 1 ACCORDING TO EN 10204 - 2.2

SECTION 2 ACCORDING TO EN 10204 - 3.1

DATA STAMPA: Stamping Date	<b>30/03/18</b>	CERTIFICATO N°: Certificate number	<b>104113</b>	VERGELLA: Wire rod	<b>AT-SG3</b>	COLATA: Charge	<b>18041</b>	CLIENTE / CUSTOMER PAWLOWSKI GMBH	051362
DDT N°		Vs.Rif.Ord. / Your ref. Nr.		Ns.Rif.Ord. Our ref. Nr.		Quantità (KG) Quantity (KG)		OGGENHAUSER HAUPTSTRASSE,77	
18 BO 001215 4,00		IHRE BEST.N.123040 VOM 14.03.18		18 OC 1195 2,00		1.152,000		89522 HEIDENHEIM OGGENHAUSEN	D

### CARATTERISTICHE MECCANICHE TIPICHE DEL DEPOSITO / TYPICAL MECHANICAL PROPERTIES OF ALL-WELD METAL

SECTION 1

Rm N/mm <sup>2</sup> <b>590</b>	Rs N/mm <sup>2</sup> <b>500</b>	Al % 5d <b>26</b>	KV (J) <b>80(-40°C)</b>	Hardness (HRC)
Tensile Strength MPa	Yeld Strength MPa	Elongation Percent	Impact Test	

### ANALISI CHIMICA COLATA / CHEMICAL ANALYSIS (HEAT)

SECTION 2

C %: <b>0,069</b>	Si %: <b>0,989</b>	Mn %: <b>1,640</b>	P %: <b>0,008</b>	S %: <b>0,018</b>	Cr %: <b>0,032</b>	Mo %: <b>0,003</b>
Ni %: <b>0,031</b>	V %: <b>0,002</b>	W %:	Ti %: <b>0,0090</b>	Al %: <b>0,001</b>	Zr %: <b>0,0001</b>	Sn %: <b>0,0050</b>
Nb %:	Sb %:	As %: <b>0,0021</b>	N ppm: <b>56</b>	O ppm:	Cu* %: <b>0,148</b>	Fx =

\* = incluso rivestimento / coating included

Fx = (10P + 5 Sb + 4 Sn + As) / 100 (elements in ppm)

### CARATTERISTICHE FINALI DEL PRODOTTO / FINAL CHARACTERISTICS OF THE PRODUCT

TIPO: <b>AT-SG3</b>	DIAMETRO <b>D.1,00</b>	RIVESTIMENTO: <b>X</b>	Ramato / Coppered
Type	(mm):	Coating	Bronzato / Bronzed
			Extra / Non ramato / Uncoppered

MIG/TIG: **M**

**CLASSIFICAZIONI:** SFA-AWS A5.18 ER70S-6  
Classifications EN ISO 14341-A- G 46 4 C1/M21 4Si1

**Articolo Cliente:**  
Customer Code:

Member of CISQ Federation

Certified Quality System  
According to **UNI EN ISO 9001:2015**  
Certificate n° 300/96/S

**ITALFIL S.p.A.**  
Quality Assurance Manager

R.A.Q. R.C.Q.  
P.I. DALLA VECCHIA ANDREA  
*Andrea Dalla Vecchia*



0045

06

DoP n° DM010

DIN EN 13479 + DIN EN ISO

Use in metallic structures or in composite metal and concrete structures