

TEST CERTIFICATE

Chemical Composition Prepared according to EN 10204 3.1
Mechanical Properties Prepared according to EN 10204 2.2

Certificate No 540959	Date 25.01.2021	Dispatch No 2021000001321
Customer ALUNOX SCHWEISSTECHNIK GMBH		Lot Class
Product Name MG 3	Approvals DB, DNV-GL, TUV	
Standards AWS/ASME SFA - 5.18 ER70S-6, EN ISO 14341 - A G 46 4 C1 G 4Si1, EN ISO 14341 - A G 46 4 M21 G 4Si1, TS EN ISO 14341 - A G 46 4 C1 G 4Si1, TS EN ISO 14341 - A G 46 4 M21 G 4Si1		

Solid Wire/Chemical Analysis(%)

Lot No	Diameter (mm)	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	V	Ti	Al	Zr
34406507	0.80	0,075	0,88	1,666	0,008	0,013	0,041	0,01	0,005	0,063	0,009	0,005	0,008	0,005
34505427	1.00	0,072	0,914	1,618	0,005	0,011	0,045	0,007	0,004	0,06	0,009	0,006	0,016	0,006
34505428	1.00	0,067	0,927	1,626	0,007	0,013	0,037	0,007	0,004	0,061	0,009	0,005	0,012	0,006
34510195	1.00	0,073	0,883	1,619	0,009	0,013	0,043	0,013	0,006	0,064	0,009	0,005	0,01	0,005
34510196	1.00	0,065	0,813	1,635	0,007	0,01	0,04	0,013	0,005	0,062	0,007	0,004	0,007	0,005
34510201	1.00	0,079	0,895	1,618	0,007	0,013	0,043	0,012	0,004	0,062	0,009	0,005	0,009	0,006
34510201	1.00	0,079	0,895	1,618	0,007	0,013	0,043	0,012	0,004	0,062	0,009	0,005	0,009	0,006

All-Weld-Metal Mechanical Properties - (Gas C1)

Production No	Diameter(mm)	Quantity(kg)	Tensile Strength (N/mm ²)	Yield Strength (N/mm ²)	Elongation(%)	Impact Energy(J)(-40)
34406507	0.80	1065	570	460	30	70
34505427	1.00	1080	570	460	30	70
34505428	1.00	3240	570	460	30	70
34510195	1.00	1080	570	460	30	70
34510196	1.00	1000	570	460	30	70
34510201	1.00	1080	570	460	30	70
34510201	1.00	2160	570	460	30	70

We hereby certify that the product described above "complies with the term of the order" and "conforms with the related international standards."

Certification Services



TEST CERTIFICATE

Chemical Composition Prepared according to EN 10204 3.1
 Mechanical Properties Prepared according to EN 10204 2.2

Certificate No 539768	Date 03.01.2021	Dispatch No 202100000009
Customer ALUNOX SCHWEISSTECHNIK GMBH		Lot Class
Product Name MG 3	Approvals DB, DNV-GL, TUV	
Standards AWS/ASME SFA - 5.18 ER70S-6, EN ISO 14341 - A G 46 4 C1 G 4Si1, EN ISO 14341 - A G 46 4 M21 G 4Si1, TS EN ISO 14341 - A G 46 4 C1 G 4Si1, TS EN ISO 14341 - A G 46 4 M21 G 4Si1		

Solid Wire/Chemical Analysis(%)

Lot No	Diameter (mm)	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	V	Ti	Al	Zr
34406502	1.20	0,075	0,91	1,654	0,009	0,013	0,032	0,009	0,003	0,062	0,01	0,005	0,008	0,005
34406504	1.20	0,078	0,858	1,682	0,009	0,012	0,032	0,01	0,004	0,061	0,008	0,004	0,007	0,005
34406506	1.00	0,076	0,888	1,665	0,01	0,013	0,043	0,009	0,006	0,062	0,009	0,005	0,008	0,005
34406507	1.20	0,075	0,88	1,666	0,008	0,013	0,041	0,01	0,005	0,063	0,009	0,005	0,008	0,005
34502683	1.20	0,075	0,899	1,649	0,007	0,011	0,032	0,008	0,003	0,068	0,009	0,005	0,01	0,005
34505428	1.20	0,068	0,925	1,62	0,007	0,013	0,037	0,006	0,004	0,061	0,009	0,005	0,013	0,006
34505430	1.00	0,072	0,923	1,625	0,01	0,013	0,036	0,005	0,003	0,06	0,01	0,006	0,014	0,006
34510193	1.00	0,068	0,871	1,617	0,008	0,011	0,044	0,013	0,005	0,065	0,009	0,005	0,011	0,006
34510194	1.00	0,073	0,89	1,611	0,006	0,011	0,041	0,013	0,005	0,063	0,009	0,005	0,011	0,006
34510195	1.00	0,073	0,883	1,619	0,009	0,013	0,043	0,013	0,006	0,064	0,009	0,005	0,01	0,005
34510202	1.00	0,079	0,88	1,617	0,008	0,012	0,044	0,013	0,006	0,064	0,009	0,005	0,01	0,006

All-Weld-Metal Mechanical Properties - (Gas C1)

Production No	Diameter(mm)	Quantity(kg)	Tensile Strength (N/mm2)	Yield Strength (N/mm2)	Elongation(%)	Impact Energy(J)(-40)
34406502	1.20	1080	570	460	30	70
34406504	1.20	1080	570	460	30	70
34406506	1.00	2160	570	460	30	70
34406507	1.20	1080	570	460	30	70
34502683	1.20	2160	570	460	30	70
34505428	1.20	1080	570	460	30	70
34505430	1.00	2160	570	460	30	70
34510193	1.00	2160	570	460	30	70
34510194	1.00	1000	570	460	30	70
34510195	1.00	1080	570	460	30	70
34510202	1.00	1080	570	460	30	70

We hereby certify that the product described above "complies with the term of the order" and "comforms with the related international standards."

Certification Services

