

TEST CERTIFICATE

Chemical Composition Prepared according to EN 10204 3.1
 Mechanical Properties Prepared according to EN 10204 2.2

Certificate No 542784	Date 23.02.2021	Dispatch No 2021000003370
Customer ALUNOX SCHWEISSTECHNIK GMBH		Lot Class
Product Name MG 2	Approvals ABS, CWB, DB, DNV-GL, HAKC, HAKC(1.00mm), HAKC(1.20mm), HAKC(1.60mm), RINA, TL, TUV	
Standards AWS/ASME SFA - 5.18 ER70S-6, EN ISO 14341 - A G 42 3 C1 G 3Si1, EN ISO 14341 - A G 42 4 M21 G 3Si1, TS EN ISO 14341 - A G 42 3 C1 G 3Si1, TS EN ISO 14341 - A G 42 4 M21 G 3Si1		

Solid Wire Chemical Analysis(%)

Lot Num	Diameter (mm)	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	V	Ti	Al	Zr
23112357	0.80	0,064	0,92	1,444	0,001	0,011	0,029	0,015	0,003	0,075	0,007	0,002	0,008	0,005
23122352	0.80	0,071	0,917	1,485	0,001	0,011	0,038	0,018	0,004	0,096	0,008	0,003	0,008	0,005
23122354	0.80	0,063	0,92	1,468	0,002	0,01	0,04	0,022	0,005	0,095	0,008	0,003	0,01	0,005
24331237	1.00	0,071	0,874	1,469	0,003	0,014	0,022	0,022	0,002	0,07	0,008	0,002	0,011	0,005
24331237	1.20	0,071	0,874	1,469	0,003	0,014	0,022	0,022	0,002	0,07	0,008	0,002	0,011	0,005
24331239	1.00	0,075	0,873	1,472	0,004	0,015	0,021	0,023	0,002	0,07	0,008	0,002	0,008	0,005
24331239	1.20	0,075	0,873	1,472	0,004	0,015	0,021	0,023	0,002	0,07	0,008	0,002	0,008	0,005
34511365	1.00	0,074	0,864	1,466	0,008	0,013	0,048	0,011	0,02	0,064	0,008	0,004	0,01	0,005
34511368	1.00	0,075	0,868	1,476	0,009	0,015	0,06	0,01	0,006	0,067	0,008	0,004	0,009	0,005
34609383	1.00	0,07	0,886	1,477	0,005	0,01	0,022	0,005	0,003	0,063	0,008	0,005	0,009	0,005
34609387	1.00	0,073	0,871	1,466	0,005	0,011	0,024	0,008	0,003	0,065	0,008	0,005	0,008	0,005
34609389	1.00	0,08	0,879	1,438	0,003	0,01	0,023	0,007	0,003	0,062	0,008	0,005	0,008	0,005
34609390	1.00	0,078	0,887	1,439	0,007	0,011	0,024	0,006	0,003	0,064	0,008	0,004	0,008	0,005
34609394	1.00	0,077	0,911	1,445	0,005	0,012	0,018	0,005	0,003	0,065	0,009	0,005	0,009	0,006

All-Weld-Metal Mechanical Properties - (Gas M21)

Production Number	Diameter(mm)	Quantity(kg)	Tensile Strength (N/mm2)	Yield Strength (N/mm2)	Elongation(%)	Impact Energy(J)(-40)
23112357	0.80	1080	560	460	27	75
23122352	0.80	1000	560	460	27	75
23122354	0.80	1080	560	460	27	75
24331237	1.00	2160	560	460	27	75
24331237	1.20	3240	560	460	27	75
24331239	1.00	1080	560	460	27	75
24331239	1.20	2160	560	460	27	75
34511365	1.00	1080	560	460	27	75
34511368	1.00	1080	560	460	27	75
34609383	1.00	1080	560	460	27	75
34609387	1.00	1000	560	460	27	75
34609389	1.00	1080	560	460	27	75
34609390	1.00	1000	560	460	27	75

We hereby certify that the product described above "complies with the term of the order" and "comforms with the related international standards."

Certification Services



34609394	1.00	1080	560	460	27	75
----------	------	------	-----	-----	----	----

We hereby certify that the product described above "complies with the term of the order" and "comforms with the related international standards."

Certification Services



TEST CERTIFICATE

Chemical Composition Prepared according to EN 10204 3.1
 Mechanical Properties Prepared according to EN 10204 2.2

Certificate No 542900	Date 01.03.2021	Dispatch No 2021000003810
Customer ALUNOX SCHWEISSTECHNIK GMBH		Lot Class
Product Name MG 2	Approvals ABS, CWB, DB, DNV-GL, HAKC, HAKC(1.00mm), HAKC(1.20mm), HAKC(1.60mm), RINA, TL, TUV	
Standards AWS/ASME SFA - 5.18 ER70S-6, EN ISO 14341 - A G 42 3 C1 G 3Si1, EN ISO 14341 - A G 42 4 M21 G 3Si1, TS EN ISO 14341 - A G 42 3 C1 G 3Si1, TS EN ISO 14341 - A G 42 4 M21 G 3Si1		

Solid Wire Chemical Analysis(%)

Lot Num	Diameter (mm)	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	V	Ti	Al	Zr
23012143	0.80	0,069	0,874	1,458	0,002	0,013	0,024	0,016	0,005	0,085	0,007	0,003	0,008	0,005
23012556	1.00	0,069	0,868	1,45	0,002	0,01	0,038	0,024	0,007	0,117	0,008	0,002	0,011	0,005
23012566	1.00	0,065	0,8	1,51	0,003	0,01	0,037	0,025	0,006	0,12	0,006	0,002	0,008	0,004
23122353	0.80	0,068	0,869	1,502	0,002	0,01	0,039	0,02	0,005	0,097	0,007	0,003	0,008	0,005
23122464	1.00	0,071	0,963	1,431	0,001	0,01	0,036	0,016	0,004	0,084	0,008	0,003	0,012	0,006
34511370	1.00	0,072	0,856	1,465	0,008	0,012	0,048	0,011	0,005	0,068	0,009	0,004	0,01	0,005
34609380	1.00	0,065	0,852	1,48	0,006	0,013	0,021	0,005	0,002	0,062	0,008	0,004	0,007	0,005
34609380	1.00	0,065	0,852	1,48	0,006	0,013	0,021	0,005	0,002	0,062	0,008	0,004	0,007	0,005
34609381	1.00	0,07	0,857	1,474	0,005	0,012	0,026	0,006	0,003	0,064	0,008	0,004	0,007	0,005
34609381	1.20	0,07	0,857	1,474	0,005	0,012	0,026	0,006	0,003	0,064	0,008	0,004	0,007	0,005
34609381	1.20	0,07	0,857	1,474	0,005	0,012	0,026	0,006	0,003	0,064	0,008	0,004	0,007	0,005
34609387	1.20	0,073	0,871	1,466	0,005	0,011	0,024	0,008	0,003	0,065	0,008	0,005	0,008	0,005
34609388	1.00	0,073	0,853	1,456	0,006	0,01	0,023	0,006	0,003	0,063	0,008	0,004	0,007	0,005
34609389	1.00	0,08	0,878	1,439	0,003	0,01	0,022	0,007	0,003	0,062	0,008	0,005	0,008	0,005
34609392	1.20	0,067	0,874	1,469	0,004	0,012	0,019	0,007	0,003	0,065	0,008	0,005	0,007	0,005
34609393	1.20	0,068	0,888	1,476	0,005	0,013	0,016	0,007	0,003	0,068	0,008	0,004	0,007	0,005

All-Weld-Metal Mechanical Properties - (Gas M21)

Production Number	Diameter(mm)	Quantity(kg)	Tensile Strength (N/mm2)	Yield Strength (N/mm2)	Elongation(%)	Impact Energy(J)(-40)
23012143	0.80	2160	560	460	27	75
23012556	1.00	500	560	460	27	75
23012566	1.00	500	560	460	27	75
23122353	0.80	1000	560	460	27	75
23122464	1.00	500	560	460	27	75
34511370	1.00	1080	560	460	27	75
34609380	1.00	1000	560	460	27	75
34609380	1.00	4320	560	460	27	75
34609381	1.00	1080	560	460	27	75
34609381	1.20	1080	560	460	27	75
34609381	1.20	1080	560	460	27	75

We hereby certify that the product described above "complies with the term of the order" and "comforms with the related international standards."

Certification Services



34609387	1.20	2160	560	460	27	75
34609388	1.00	1080	560	460	27	75
34609389	1.00	1080	560	460	27	75
34609392	1.20	1080	560	460	27	75
34609393	1.20	1080	560	460	27	75

We hereby certify that the product described above "complies with the term of the order" and "comforms with the related international standards."

Certification Services



TEST CERTIFICATE

Chemical Composition Prepared according to EN 10204 3.1
 Mechanical Properties Prepared according to EN 10204 2.2

Certificate No 546454	Date 27.04.2021	Dispatch No 2021000007593
Customer ALUNOX SCHWEISSTECHNIK GMBH		Lot Class
Product Name MG 2	Approvals ABS, CWB, DB, DNV-GL, HAKC, HAKC(1.00mm), HAKC(1.20mm), HAKC(1.60mm), RINA, TL, TUV	
Standards AWS/ASME SFA - 5.18 ER70S-6, EN ISO 14341 - A G 42 3 C1 G 3Si1, EN ISO 14341 - A G 42 4 M21 G 3Si1, TS EN ISO 14341 - A G 42 3 C1 G 3Si1, TS EN ISO 14341 - A G 42 4 M21 G 3Si1		

Solid Wire Chemical Analysis(%)

Lot Num	Diameter (mm)	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	V	Ti	Al	Zr
23022170	1.20	0,07	0,882	1,461	0,002	0,014	0,022	0,013	0,004	0,074	0,007	0,002	0,008	0,005
34510232	1.20	0,072	0,856	1,458	0,005	0,011	0,039	0,012	0,005	0,066	0,008	0,005	0,01	0,005
34511369	1.00	0,069	0,856	1,469	0,01	0,012	0,059	0,013	0,005	0,071	0,008	0,004	0,009	0,005
34511371	1.00	0,078	0,88	1,456	0,006	0,013	0,048	0,014	0,006	0,067	0,009	0,004	0,011	0,006
34609379	1.00	0,065	0,869	1,465	0,007	0,012	0,023	0,006	0,003	0,062	0,008	0,004	0,007	0,005
34609384	1.00	0,067	0,867	1,467	0,007	0,011	0,023	0,005	0,003	0,065	0,008	0,005	0,008	0,005
34609385	1.00	0,074	0,869	1,46	0,006	0,011	0,024	0,006	0,003	0,063	0,008	0,005	0,008	0,005
34609386	1.00	0,068	0,868	1,462	0,008	0,011	0,028	0,011	0,003	0,066	0,008	0,004	0,008	0,005
34609387	1.00	0,071	0,869	1,477	0,005	0,011	0,025	0,008	0,003	0,065	0,008	0,005	0,008	0,005
34609388	1.00	0,071	0,848	1,472	0,007	0,011	0,024	0,006	0,003	0,063	0,008	0,004	0,007	0,005
34609392	1.00	0,065	0,876	1,476	0,004	0,012	0,019	0,007	0,003	0,065	0,008	0,005	0,007	0,005

All-Weld-Metal Mechanical Properties - (Gas M21)

Production Number	Diameter(mm)	Quantity(kg)	Tensile Strength (N/mm2)	Yield Strength (N/mm2)	Elongation(%)	Impact Energy(J)(-40)
23022170	1.20	1080	560	460	27	75
34510232	1.20	1080	560	460	27	75
34511369	1.00	1080	560	460	27	75
34511371	1.00	1080	560	460	27	75
34609379	1.00	1080	560	460	27	75
34609384	1.00	1080	560	460	27	75
34609385	1.00	2160	560	460	27	75
34609386	1.00	1080	560	460	27	75
34609387	1.00	1080	560	460	27	75
34609388	1.00	1080	560	460	27	75
34609392	1.00	3240	560	460	27	75

We hereby certify that the product described above "complies with the term of the order" and "comforms with the related international standards."

Certification Services

