

Lincoln Electric Europe B.V.

Nieuwe Dukenburgseweg 20
6534 AD Nijmegen
Netherlands

Phone: +33 1 342 13 333
Fax : +33 1 342 13 130
Internet : www.lincolnelectriceurope.com



1 1

LINCOLN ELECTRIC BESTER SP. Z O.O.

2051500930096929

17/12/18

Spider

SPEZIAL 3.20X0350XCBOX

EN ISO 2560-A : E 38 3 B 12 H10
AWS A 5.1 - E 7016-H8

M1MS182279

/

EN 10 204-3.1 WELD METAL

C	Mn	Si	P	S	Cr	Ni	Mo	Nb	V
0.046	0.893	0.526	0.014	0.008	0.033	0.048	0.004	0.001	0.007
Cu									
0.078									

/

EN 10 204-2.2 WELD METAL

				Z			
°C	Rp0.2 N/mm ²	N/mm ²	%	%	°C	Joule (Charpy-V)	
+20	446	533	29		-20	102	As Welded
					-30	92	

04.02.2019

/

Miroslav Kusnir
Air Liquide Welding Central Europe
Tel: +421/ 37 692 46 39
Fax: +421/37 651 2804

Bogdan Serban
QA Manager – Buzau Plant